



DIV-POLYMER d.o.o.  
za proizvodnju, trgovinu i usluge export - import Bačka Palanka  
Novosadski put 21, 21400 Bačka Palanka, Republika Srbija  
Tel: +381 (0) 63 539896, Mail: dragutin.knezevic@divpolymer.com

## PP STAPLE FIBRE dtex 17

	<b>UNIT OF MEASURE</b>	<b>DECLARED VALUE</b>
Fineness:	Dtex	17 +/- 10%
cV Fineness:	%	Min 5 /max 30
Cut length:	Mm	60,75 ,90 +/- 10%
Tensile strength at break:	Cn/dtex	2,6 – 3,5
cV Tensile strength at break:	%	Min 5 /max 30
Tensile elongation at break:	%	Min 80 /max 190
cV Tensile elongation at break:	%	Min 10 /max 80
Preparation content:	%	0,4-0,9
Crimp no:	At 10 mm	3-5
Bonding:	%	Min 0 /max 0,15
Color:	According to agreed reference sample	Min. 4
Thermostability at 130° C/ max:	%	Min 2 /max 5
Moisture content:	%	0,10