



DIV-POLYMER d.o.o.
za proizvodnju, trgovinu i usluge export - import Bačka Palanka
Novosadski put 21, 21400 Bačka Palanka, Republika Srbija
Tel: +381 (0) 63 539896, Mail: dragutin.knezevic@divpolymer.com

PP STAPLE FIBRE dtex 6,7

Customer (ALTEX) article no.: 50038

	UNIT OF MEASURE	DECLARED VALUE
Fineness:	Dtex	6,7+/- 10%
cV Fineness:	%	Min 5 / max 30
Cut length:	Mm	75 +/- 10%
Melt Flow Index (MFI)	g/10 min	12
Tensile strength at break:	Cn/dtex	3.8-4,7
cV Tensile strength at break:	%	Min 10 /max 30
Tensile elongation at break:	%	Min 80 /max 160
cV Tensile elongation at break:	%	Min 40 /max 80
Preparation content:	%	0,2-1,25
Crimp no:	At 10 mm	3-5
Bonding:	%	Min 0 /max 0,15
Color:	According to agreed reference sample	Min. 4
Thermostability at 130° C/ max:	%	Min 2 / max 5
Moisture content:	%	0,10