



DIV-POLYMER d.o.o.  
za proizvodnju, trgovinu i usluge export - import Bačka Palanka  
Novosadski put 21, 21400 Bačka Palanka, Republika Srbija  
Tel: +381 (0) 63 539896, Mail: dragutin.knezevic@divpolymer.com

## PP STAPLE FIBRE dtex 70

	<b>UNIT OF MEASURE</b>	<b>DECLARED VALUE</b>
Fineness:	Dtex	70+/- 10%
cV Fineness:	%	Min 5 /max 30
Cut length:	Mm	60, 75, 90 +/- 10%
Tensile strength at break:	Cn/dtex	2,6 – 3,5
cV Tensile strength at break:	%	Min 5 / max 30
Tensile elongation at break:	%	Min 80 / max 190
cV Tensile elongation at break:	%	Min 20 /max 80
Preparation content:	%	0,2-0,8
Crimp no:	At 10 mm	1-3
Bonding:	%	Min 0 /max 0,15
Color:	According to agreed reference sample	Min. 4
Thermostability at 130° C/ max:	%	Min 2 / max 5
Moisture content:	%	0,10