



DIV-POLYMER d.o.o.  
 za proizvodnju, trgovinu i usluge export - import Bačka Palanka  
 Novosadski put 21, 21400 Bačka Palanka, Republika Srbija  
 Tel: +381 (0) 63 539896, Mail: dragutin.knezevic@divpolymer.com

## PP STAPLE FIBRE dtex 8,8 Micro fibers

	UNIT OF MEASURE	DECLARED VALUE
Fineness:	Dtex	8,8 +/- 10%
cV Fineness:	%	Max 30
Cut length:	Mm	6, 9, 12,15, 18 +/- 10%
Tensile strength at break:	Cn/dtex	3,5-4,2
cV Tensile strength at break:	%	Max 30
Tensile elongation at break:	%	Max 160
cV Tensile elongation at break:	%	Max 80
Preparation content:	%	0,4-1,25
Crimp no:	At 10 mm	/
Bonding:	%	Max 0,15
Color:	According to agreed reference sample	Min. 4
Thermostability at 130° C/ max:	%	Max 5
Moisture content:	%	0,10